



Preparation

- The best temperature for EkoStrip solution is 80°F to 100°F
- Not to exceed 100°F
- Be sure you use in a well ventilated area
- Gather all supplies needed before starting your project

Directions

- Use full strength
- Apply EkoStrip by spraying, brushing or rolling onto surface
- Apply a 1/8" thick coating of EkoStrip to the paint surface only
- Cover with plastic to reduce evaporation if necessary
- The stripping time will depend on the air temperature, preferably in the 90°F range
- A reaction should occur in 2-4 hours at the recommended temperature
- If paint is resistant the stripper can be left on overnight
- Remove stripper and paint coating with a pressure washer. (hot if possible)
- Rinse in cold water

Storage

- Store in a cool dry place at room temperature
- Keep out of direct sunlight
- Keep lid tight at all times
- Do not allow material to freeze
- Use within one year of purchase